

# Product Information Sheet

**WIPE OFF**™

## Aqualine AntiFlyposter Coating™ [Ref.: WGS18/T5]

**Description:** A non hazardous, water based coating based on a special blend of Waxes and Acrylic resins. The combination provides a high degree of anti-stick properties in a simple to apply coating which has excellent adhesion to metal, wood, brick, painted metal, concrete and similar surfaces. Even posters applied with high strength pastes will peel off easily and cleanly.

### Properties:

Specific Gravity	1.01 gm/ml
Appearance	Thickened gel
Colour	Clear
Number of coats	One or Two coats depending on the porosity of the Surface.
Cleaner	Water
Flash Point	Non Flammable
Drying Times	
Touch	35 - 45 minutes [ 20°C., 60% RH]
Hard	12 hours
Overcoating	1.5 to 2 hours [20°C., 60% RH]
Coverage Rate	Circa 3 to 5 square metres per Litre [ Very dependant upon surface type and its porosity]

### Application Methods

**IMPORTANT! Stir well before use.**

Brush or roller. Apply generously onto the area to be treated with a brush. Even out the surface by gently brushing at right angles to the original application. Do not over brush.

Best applied with either a short haired roller or open textured foam roller, or brush.

Surfaces must be clean of all debris and contamination. Do not apply to unsound surfaces. Apply when the relative humidity is below 80% RH. For external application only apply at temperatures above 5°C when rain is unlikely during application or drying.

### Cleaning

Clean spillage's and equipment with clean water and/or warm soapy water.

## **Storage**

Store in covered, ventilated areas out of direct sunlight between 5 & 25<sup>o</sup> C.. Keep away from frost.

## **Safety Data**

Not classified as hazardous however we recommend the use of plastic gloves and safety glasses when using the product.

**Note: The information given above is, to the best of our knowledge, true and accurate. However it is given as a guidance only and is not to be taken as a warranty of the results.**

**Aqualine (Coatings) Limited, Unit 33, Business & Innovation Centre, Sunderland Enterprise Park East,  
Wearfield, Sunderland. SR5 2TA.**

**Tel: +44 (0) 191 516 6232. Fax: +44 (0) 191 516 6005. Email: [info@aqualine-coatings.co.uk](mailto:info@aqualine-coatings.co.uk)**

**Website: <http://www.aqualine-coatings.co.uk>**